

# Pliobond® Special Purpose Contact Adhesives

## Traditional and VOC Compliant Formulations

Pliobond provides permanent, flexible bonding and will not get brittle with age. The product resists most acids, gasoline, oil, grease and water.

Traditional formulations employ an MEK solvent and the VOC compliant versions use a blended solvent.


Pliobond 20, 25, 30, and 35 are all purpose, thermosetting contact adhesives with solid contents of pigment reinforced synthetic rubber and synthetic plastic resin. The 20 and 25 versions are most frequently used and contain 20 percent

solids while the 30 and 35 products contain 30 percent solids and form a heavier film with controlled penetration. The latter are most often used on more porous surfaces. The 25, 35 and 45 versions are VOC compliant formulas.

Pliobond 45 consists of 40 percent solids and is available on special orders.

Pliobond HT-30 has the same qualities as Pliobond 30 but it resists higher temperatures while providing permanent flexible bonding. However, it must be heat cured to 300 degrees F.

## Proven Professionally—Everyday



**THE RUSCOE COMPANY**

Adhesives & Sealants

## GENERAL INFORMATION

Many shops and plants with variable production and short runs require a versatile adhesive. For these and for “spot-use” applications, PLIOBOND adhesives simplify warehousing and inventory. They produce strong serviceable joints with most materials. The cement is supplied ready to use and requires no conditioning agents, accelerators, or catalysts.

A single method, called wet bond-

ing, can be used for joining virtually all materials with PLIOBOND.

For wet bond: coat both surfaces, allow to dry to a tack free state, recoat one surface then assemble the parts when tacky. Test before use to ensure compatibility with both adherents.

An initial set takes place in PLIOBOND adhesive joints as soon as most of the solvent has evaporated.

The strength of this initial set is usually sufficient to maintain the assembly, and with some adherents, will exceed the strength of the material. Bond strength increases as evaporation of the solvent progresses, reaching a maximum when all solvent has been removed.

In addition to the adhesive applications, PLIOBOND is also used as a primer, coater, and sealer.

**HANDLING:** PLIOBOND adhesives contain ingredients which could be harmful if mishandled. Contact with skin and eyes should be avoided and necessary protective equipment and clothing should be worn.

For important health, safety and handling information,

consult the Material Safety Data Sheet for each individual adhesive before use.

**SHELF LIFE:** 12 month in closed containers under ambient conditions (rotate stock). D.O.T. label required: flammable liquid. Stir before use.

Physical properties of PLIOBOND VOC Compliant special purpose contact adhesives			
Table 1	PLIOBOND 25	PLIOBOND 35	PLIOBOND 45
Base Polymer	Nitrile Rubber		
Base Resin	Thermosetting Phenolic		
Total Solids, %	18-22	28-32	37-42
Viscosity, Cps	400-1200	5,000-10,000	32,500-77,500
Specific Gravity	0.87	0.89	0.99
Pounds/Gallon	7.2	7.4	7.7
Color	Tan	Tan	Tan
Solvent(S)	Blend	Blend	Blend
Flash Point, °F Seta	20	20	20

### VOC Compliant Formulation

#### PLIOBOND 45

PC-445 Gallon Can  
PC-545 5-Gallon Pail  
PC-5045 50-Gallon Drum

#### PLIOBOND 25 LV

P-612-LV 3-oz. Skin-Pack Brush-top Bottle  
PBC-25-LV ½-Pint Brush-top Can  
PC-225-LV Pint Can  
PC-325-LV Quart Can  
PC-425-LV Gallon Can  
PC-525-LV 5-Gallon Pail  
PC-5025-LV 50-Gallon

#### PLIOBOND 35 LV

PBC-35-LV ½-Pint Brush-top Can  
PC-235-LV Pint Can  
PC-335-LV Quart Can  
PC-435-LV Gallon Can  
PC-535-LV 5-Gallon Pail  
PC-5035-LV 50-Gallon Drum

**Distributed By:**

Physical properties of PLIOBOND Traditional formulation special purpose contact adhesives			
Table 1	PLIOBOND 20	PLIOBOND 30	PLIOBOND HT-30
Base Polymer	Nitrile Rubber		
Base Resin	Thermosetting Phenolic		
Total Solids, %	18-22	28-32	30
Viscosity, Cps	400-1200	5,000-10,000	4,000
Specific Gravity	0.87	0.89	0.89
Pounds/Gallon	7.2	7.4	7.4
Color	Tan	Tan	Tan
Solvent(S)	MEK	MEK	MEK/Alcohol
Flash Point, °F Seta	20	20	21

### Traditional Formulation

#### Consumer Packages

#### PLIOBOND 20

P-141 1 oz. Tube Blister  
P-612 3 oz. Brush Top Bottle  
PBC-20 ½ pint Brush Top Can

#### Industrial Packages

#### PLIOBOND 20

P351 1 oz. tube Ind. Pack  
PBC-20 ½ pint brush top can  
PC-220 Pint Can  
PC-320 Quart Can  
PC-420 Gallon Can  
PC-520 5-Gallon Pail  
PC-5020 50-Gallon Drum

#### Industrial Packages

#### PLIOBOND 30

P-3530 1 oz. tube Ind. Pack  
PBC-30 ½ pint brush top can  
PC-230 Pint Can  
PC-330 Quart Can  
PC-430 Gallon Can  
PC-530 5-Gallon Pail  
PC-5030 50-Gallon Drum

#### PLIOBOND HT-30

PC-HT230 Pint Can  
PC-HT330 Quart Can  
PHT 30-4 Gallon Can  
PHT30-5 5-Gallon Pail

## Proven Professionally—Everyday



**THE RUSCOE COMPANY**

Adhesives & Sealants

Order from:

**The Ruscoe Company**  
485 Kenmore Blvd.  
Akron, Ohio 44301

330.253.8148

800.293.8148

Fax: 330.253.2933

www.ruscoec.com

Email: sales@ruscoe.com

Manufactured by:

**Ashland Chemical, Inc.**

Subsidiary of Ashland Oil, Inc.

PLIOBOND® Registered trademark,  
Ashland Oil, Inc.